


Eco-friendly High-performance Knit Fabric

Airshut™ MP

An eco-friendly and highly functional coated knit fabric with high moisture permeability and low condensation. Airshut® MP reduces the feeling of stuffiness and provides a comfortable dry touch clothing environment.



*1 The soft texture suppresses the fabric rubbing sound.

Basic performance

Water repellency	JIS L1092 spray method	: Initial stage ≥ 4th grade
Breathability	JIS L1096 A Frazier method	: Initial stage ≤ 5cm ³ /cm ² / sec.
Moisture permeability	JIS L1099 A-1 method	: ≥ 4,000g /m ² / 24hrs
	JIS L1099 B-1 method	: ≥ 30,000g /m ² / 24hrs



KOMATSU MATERE Co.,Ltd.


Head Office Nu 167 Hama-machi, Nomi-city, Ishikawa, Japan TEL : +81-761-55-1111
 Tokyo Sales Branch Maruito Ginza No.3 Building 4F, 3-10-6 Ginza, Chuo-ward, Tokyo, Japan TEL: +81-3-3549-3880
 Osaka Sales Branch HERBIS ENT Office Tower 8F, 2-2-22 Umeda, Kita-ward Osaka-city, Osaka, Japan TEL: +81-6-6344-4161



Airshut MP WEBSITE

环保型高机能性针织物 Airshut™ MP

环保型高机能性的涂层针织物，兼具有高导湿性和低结露性。
可减少闷热感，提供干爽的触感和舒适的衣内环境。



*1) 质地柔软, 可抑制面料摩擦时产生的噪音。

基本性能

不沾水性 JIS L1092 喷雾法	: 初始值 \geq 4 级
透气性 JIS L1096 A 弗雷泽型	: 初始值 \leq 5 $\text{cm}^3 / \text{cm}^2 / \text{sec}$.
导湿性 JIS L1099 A-1 法	: $\geq 4,000 \text{g} / \text{m}^2 / 24\text{hrs}$
JIS L1099 B-1 法	: $\geq 30,000 \text{g} / \text{m}^2 / 24\text{hrs}$



KOMATSU MATERE Co., Ltd.

总 公 司 - 石川县能美市浜町NU167番地 TEL: +81-761-55-1111

东京营业所 - 东京都中央区银座3丁目10番6号 MARUITO 银座3号大厦 4楼 TEL: +81-3-3549-3880

大阪营业所 - 大阪府大阪市北区梅田2丁目2番22号 HERBIS ENT 办公楼8楼 TEL: +81-6-6344-4161

上海代表处 - 中华人民共和国上海市延安西路2201号 上海国际贸易中心 1913室 TEL: +86-21-6275-4558



Airshut MP

WEBSITE